

# A·R·C·H·I·T·E·C·T·U·R·A·L

## ROOF COATINGS

### ● **PRODUCT DATA SHEET**

# HydroSHIELD T2S R. I. P.

#### **DESCRIPTION**

HydroSHIELD T2S RIP is a water based rust inhibitive primer. This acrylic primer dries by dehydration. HydroSHIELD T2S RIP adheres to metallic and corroded carbon steel. Use over lightly rusted steel. Cover over with ARC HydroSHIELD T2S Quick Set coating and sealants within 72 hours. Is U.V. stable.

#### **RECOMMENDED USES**

HydroSHIELD T2S RIP to be applied to corroded metal surfaces. Allow to completely cure before application of the ARC coating.

#### **APPLICATION**

Apply when ambient temperature is 50° F and rising. Surface to be treated must be clean. If necessary, remove all dust, grease and loose debris before applying this product. Apply HydroSHIELD T2S RIP by roller, brush or spray at a rate of 1 gallon per 200 square feet. Multiple passes may be applied waiting 2 hours between applications when applied at ambient temperature of 70° F and rising.

#### **BENEFITS**

- Anti Corrosion Protection
- Stops Rust
- Excellent Primer
- Non-Toxic
- Easy Clean Up
- Prevents Rust

#### **TECHNICAL DATA**

COLOR:	Yellow
VISCOSITY:	5000 - 6000 cps +/- 5%
FUNGAL RESISTANCE:	Passed ASTM D-3273-73T
CLEAN UP:	Soap and water
APPLICATION RATE:	200 square feet per gallon
DRY TIME: (dehydration)	2 hours @ 70° F
SOLIDS BY WEIGHT:	55% +/- 5% ASTM D- 1644
SOLIDS BY VOLUME:	48% +/- 5% ASTM D- 2697
VOC:	<50 grams per liter
WEIGHT:	8.6 lbs. per gallon +/- 5%

**PRECAUTION: If rain or fog is expected within 24 hours, DO NOT APPLY. This product sets by dehydration. Do NOT leave in spray hose overnight. FLUSH SPRAY LINES.**

*Not recommended to use HydroSHIELD T2S Activator to set HydroSHIELD T2S R.I.P.*

There is no warranty given, expressed or implied, through the values or statements made here, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by our in house and independent third party labs in order to obtain approval and/or classification. Acceptance, purchase and selection of these products are the sole responsibility of the buyer, buyer's agent, or the buyer's customer. ARC assumes no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER GUARANTY OR WARRANTY OF ANY KIND IS MADE BY ACE ROOF COATINGS, INC. OR ITS SUBSIDIARIES, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.