

A·R·C·HITECTURAL

ROOF COATINGS

● PRODUCT DATA SHEET

HydroSHIELD T₂S STANDARD

DESCRIPTION

HydroSHIELD T2S White Standard is a water based acrylic designed to be used with HydroSHIELD T2S Catalyst. This acrylic coating may be dried by catalyst or ambient temperature through evaporation of water to a non- yellowing, water- repellent surface. HydroSHIELD T2S White Standard is UV stable, and has the unique property to form a dry film surface within minutes of application of HydroSHIELD Quick Set Catalyst.

RECOMMENDED USES

HydroSHIELD T2S White Standard can be applied to slope roof surfaces such as metal, masonry, wood, single ply membrane (PVC, TPO, Hypalon, SBS Smooth, or guantule rolled modified plies)and over ARC primers after following preparation procedures.

APPLICATION

Surface to be treated must be clean. If necessary, remove all dust, grease and loose debris before applying this product. When using HydroSHIELD T2S Standard spray apply at a rate of 1.00 to 1.5 gallon per 100 square feet per pass. Multiple passes may be applied waiting 2 hours between applications when T2S catalyst is not utilized.

BENEFITS

Increases Productivity	Non-Toxic
Flexible	Easy Clean Up
Non- Yellowing	Catalyst Quick Set
Energy Saving	Extends Workday
Waterproof	Resists Rain

TECHNICAL DATA

EMITTANCE:	.91 ASTM C-1371
REFLECTANCE:	.80%
FLEXIBILITY:	Passed 180° Mandrel Bend Test ASTM D-822
VISCOSITY:	8000 cps +/- 5%
COLOR:	White
WEATHERABILITY:	Passed 4000 Hours ASTM G-53
FIRE RESISTANCE:	Class "A" ASTM E-108
FUNGAL RESISTANCE:	Passed ASTM D-3273-73T
ELONGATION:	625% at 70° F ASTM 2370 with CATALYST: 350% at 70° F ASTM 2370
CLEAN UP:	Soap and water
TENSILE:	255 psi ASTM D-2370 with CATALYST: 305 psi ASTM D-2370
PERMEABILITY:	2.5 perms ASTM D-1653A with CATALYST: 6.3 perms ASTM D-1653A
SOLIDS BY WEIGHT:	60% +/- 5% ASTM D- 1644
SOLIDS BY VOLUME:	52% +/- 5% ASTM D- 2697
VOC:	<50 grams per liter
WEIGHT:	13 lbs. per gallon

CAUTION: Without Catalyst high humidity requires a longer time for water-based coatings to form a film that is rain resistant.

T2S "Technology - Two Step" permits ARC coating to be applied over moisture, damp or dew surfaces without permitting cold wall blistering as well as develops a rain/washoff resistance within 5 minutes. Second pass of ARC coating can be applied in less than 2 hours.

There is no warranty given, expressed or implied, through the values or statements made here, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by our in house and independent third party labs in order to obtain approval and/or classification. Acceptance, purchase and selection of these products are the sole responsibility of the buyer, buyer's agent, or the buyer's customer. ARC assumes no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER GUARANTY OR WARRANTY OF ANY KIND IS MADE BY ACE ROOF COATINGS, INC. OR ITS SUBSIDIARIES, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.